

REACTION TO FIRE CLASSIFICATION REPORT N° 2022/152-2

According to EN 13501-1 (2018)

(English version of classification report N°2022/152-1)

Notification by the French Government to the European Commission under n° NB 2401
Regulation (UE) n° 305/2011

Sponsor:

UNILIN BV Division Flooring

Ooigemstraat 3 8710 Wielsbeke BELGIUM

Product name:

LVT EVF CL 4 + 1 mm / 0,30 mm /

LVT EVF CL 5 + 1 mm / 0.55 mm

Description:

Loose-laid panels (EN 16511 family)

(see detailed description in paragraph 2)

Date of issue:

01/06/2022

The indicated classification does not prejudge the conformity of marketed materials with the samples submitted to the tests and under no circumstances, this document should not be considered as type approval or certification of the product in the sense of the L 115-27 article of the consumption's code of the law.

The reproduction of this classification report is only authorised in its integral form. It comprises 4 pages

1. Introduction

This classification report defines the classification assigned to the above-mentioned products in accordance with the procedures given in the NF EN 13501-1 standard (2018).

Page 2/4

2. Details of classified product

2.1. Product standard

NF EN 14041 (2005): "Resilient, textile and laminate floor coverings - Essential characteristics".

2.2. Product description

Loose-laid panels – Semi-rigid multilayer modular floor covering (MMF) panels with wear resistant top layer (EN 16511 family) in size LVT of 303 mm x 610 mm.

Tested loose laid over a wood panel particle board without flame retarded classified $C_{\rm fl}$ -s1 with a density (680 ± 50) kg/m³ and thickness (20 ± 2) mm.

Use surface: PVC Type backing: PVC

Nominal mass per unit area: 6871 to 8050 g/m² Nominal total thickness: 5,00 to 6,00 mm Nominal wear layer thickness: 0,30 to 0,55 mm

3. Test reports and tests results in support of this classification

3.1. Tests reports

Name of laboratory	Name of sponsor	Test report N°	Test method
	UNILIN BV Division Flooring	RL 2022/272-1	NF EN ISO 9239-1
C.R.E.T.	Ooigemstraat 3	RL 2022/275-1	(EN ISO 9239-1 :2010)
	8710 Wielsbeke	RL 2022/272-2	NF EN ISO 11925-2
	BELGIUM	RL 2022/275-2	(EN ISO 11925-2:2010)

3.2. Tests results

		Number of tests	Results	
Test method	Product		Parameters	Compliance parameters
NF EN ISO 11925-2			Fs ≤ 150 mm	Compliant
Surface exposure-15 secondes	LVT EVF CL 4 + 1 mm / 0,30 mm	6	Ignition of the filter paper	Compliant

			Results	
Test method	Product	Number of tests	Parameters	Compliance parameters
NF EN ISO 11925-2			Fs ≤ 150 mm	Compliant
Surface exposure-15 secondes	LVT EVF CL 5 + 1 mm / 0,55 mm	6	Ignition of the filter paper	Compliant

				Results
Test method	Product	Number of tests	Parameters	Continuous parameters: mean value
NF EN ISO 9239-1	LVT EVF CL 4 +1 mm / 0,30 mm	3	Critical heat flux (kW/m²)	≥11
INI BIVISO 7237 I	EVI EVI CE I I IIIII I 0,50 IIIII		Smoke (% X min)	108,3

				Results
Test method	Product	Number of tests	Parameters	Continuous parameters: mean value
NF EN ISO 9239-1	LVT EVF CL 5 + 1 mm / 0,55 mm	3	Critical heat flux (kW/m²)	10,8
111 211 100 7237 1	D 1 D 1 CD 3 1 I IIII 7 0,33 IIIII	3	Smoke (% X min)	135,5

4. Classification and field of application

4.1. Reference of classification

This classification has been carried out in accordance with EN 13501-1 (2018).

4.2. Classification

Fire behaviour		Smoke production
B_{fl}	-	s1

Classification: B_{fl} - s1

4.3. Field of application

This classification is valid for the following end use applications:

Loose laid over a wood panel particle board without flame retarded classified C_{fl} -s1 with a density $\geq 510 \text{ kg/m}^3$ -and over a fibre-cement $A2_{fl}$ -s1 or $A1_{fl}$ class with a density $\geq 1350 \text{ kg/m}^3$.

This classification is valid for the following product parameters:

A nominal mass per unit area of: 6871 to 8050 g/m²

• A nominal thickness of: 5,00 à 6,00 mm

• A nominal wear layer thickness of: 0,30 to 0,55 mm

5. Limitations

This classification document does not represent type approval or certification of the product.

"The classification assigned to the product in this report is appropriate to a declaration of conformity by the manufacturer within the context of system 3 of AVCP and CE marking under the Regulation 305/2011/EU of the European Parliament and of the Council of 9 March 2011 laying down harmonised conditions for the marketing of constructions products.

The manufacturer has made a declaration, which is held on file. This confirms that the products design requires no specific processes, procedures or stages (no addition of flame-retardants, limitation of organic content, or addition of fillers) that are aimed at enhancing the fire performance in order to obtain the classification achieved. As a consequence the manufacturer has concluded that system 3 attestation is appropriate.

The test laboratory has, therefore, played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested."

Head of Tests David VANDIERDONCK For the SARL C.R.E.T. The Technical Director Marc WELCOMME

End of the classification report