

Unilin bv - Division Flooring
Ooigemstraat 3 bus 1
8710 WIELSBEKE

Your notice of
27-06-2025

Your reference

Date
22-08-2025

Analysis Report 25.03573.03

Required tests :


EN 13501-1 (2019)

Sample id	Information given by the client	Date of receipt
T2513198	Unilin LVT Rigid Click Pad 5+1 mm CL33	27-06-2025



Kristina De Temmerman
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.




Reference: T2513198 - Unilin LVT Rigid Click Pad 5+1 mm CL33

Information given by the client

Product standard	EN 13501-1 (2019)
Floor covering type	Loose-laid panels - Semi-rigid multilayer modular floor covering (MMF) panels with wear resistant top layer
EN product standard	EN 16511
FR treated	no
Mass	8109 g/m ²
Thickness	6 mm

Notified body No: 0493



Reference: **T2513198 - Unilin LVT Rigid Click Pad 5+1 mm CL33**

Reaction to fire tests – Ignitability of building products subjected to direct impingement of flame - Single-flame source test


Date of ending the test 08-08-2025
Standard used EN ISO 11925-2 (2020)
Product standard EN 13501-1 (2019)

Floor covering

Deviation from the standard -
Conditioning 23°C, relative humidity 50%
Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Weight (g/m²) 8281
Dimension of the specimens 250 mm x 90 mm x 6 mm
Substrate Fibre cement board - density (1800 ± 200) kg/m³
Mounting Loose-laid
Specimens have not been cleaned
Joint In width direction : at 20 mm and 145 mm



Flame application time (s)

15

Flame application

Surface - front

	Length			Width		
	1	2	3	4	5	6
Ignition	no	no	no	no	no	no
Time to reach 150 mm mark (s)	*	*	*	*	*	*
Additional observations						
Molten debris within 20 s after flame application	no	no	no	no	no	no
Hole formed within 20 s after flame application	no	no	no	no	no	no

* = time to reach the mark > 20 s or mark not reached


Criteria Floorcoverings

time to reach the mark:

- > 20 s : Class Efl
- \leq 20 s : Class Ffl

Classification

Class E_{fl}



Reference: T2513198 - Unilin LVT Rigid Click Pad 5+1 mm CL33

Reaction to fire tests for floorings - Determination of the burning behaviour using a radiant heat source

Date of ending the test

19-08-2025

Standard used

EN ISO 9239-1 (2010)

Product standard

EN 13501-1 (2019)

Deviation from the standard

-

Conditioning

23°C, relative humidity 50%

Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Test specimen

Substrate

Particle board - density (680 ± 50) kg/m³

Mounting


Loose-laid

Specimens have not been cleaned

Joint

In length direction : at 610 mm and at the centreline from the zero point

In width direction : at 105 mm and each 125 mm



Radiant heat flux

	Flame spread distance (mm)			Flame-out time	Critical heat flux*
	10 min	20 min	30 min		kW/m ²
Width					
#1	<110	<110	<110	12 min 00 s	≥ 11
Length					
#1	<110	<110	<110	12 min 00 s	≥ 11
#2	<110	<110	<110	12 min 00 s	≥ 11
#3	≤110	≤110	≤110	12 min 00 s	≥ 11
Mean					≥ 11

* Heat flux at the time of flame extinguishment (CHF) or after a test duration of 30 minutes (HF-30).

Fire classification in accordance with EN 13501-1 (2019)


Class	EN ISO 11925-2 or CWFT	EN ISO 9239-1 (test duration = 30 min)
B _{fl}	E _{fl}	heat flux ≥ 8,0 kW/m ²
C _{fl}	E _{fl}	heat flux ≥ 4,5 kW/m ²
D _{fl}	E _{fl}	heat flux ≥ 3,0 kW/m ²

Smoke production: Light attenuation

	Maximum (%)	Total (%.min)
Width		
#1	25	96
Length		
#1	22	107
#2	24	114
#3	23	93
Mean		105

Additional classification in accordance with EN 13501-1 (2019)

smoke production ≤ 750%.min	s1
smoke production > 750%.min	s2



Reaction to fire classification : Bfl / s1
*Loose-laid on a combustible substrate**

* *End use substrates of wood and of classes A1 and A2-s1,d0 (EN 13238:2010 § 5.2.3)*

Limitations

This classification document does not represent type approval or certification of the product.

“The classification assigned to the product in this report is appropriate to a declaration of performance by the manufacturer within the context of system 3 of assessment and verification of constancy of performance and CE marking under the Construction Products Regulation.

The manufacturer has made a declaration, which is held on file. This confirms that the products design requires no specific processes, procedures or stages (e.g. no addition of flame-retardants, limitation of organic content, or addition of fillers) that are aimed at enhancing the fire performance in order to obtain the classification achieved. As a consequence the manufacturer has concluded that system 3 attestation is appropriate.

The test laboratory has, therefore, played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested.”